

# 銅板(CuP), 黄銅板(BsP) 取扱寸法及び1枚当り重量(kg)表

銅板(CuP)				
板厚	小板定板 365X1200	大板定板 1000X2000	4×8板 1250X2500	切板
0.10	0.389			
0.15	0.584			
0.20	0.779			
0.25	0.973			
0.30	1.168			
0.35	1.363			
0.4	1.557	7.112		
0.5	1.947	8.890		
0.6	2.336	10.668		
0.7	2.726	12.446		
0.8	3.115	14.224		
0.9				
1.0	3.894	17.780	27.781	
1.2	4.673	21.336		
1.4	5.451			
1.5	5.841	26.670	41.672	
1.6	6.230	28.448		
1.8	7.009			
2.0	7.788	35.560	55.563	
2.3	8.956	40.894		
2.5	9.735	44.450		
2.6	10.124			
2.8				
3.0	11.681	53.340	83.344	○
3.2	12.460			
3.5	13.628			
4.0	15.575	71.120		○
4.5	17.522			
5.0	19.469	88.900		○
5.5				
6.0	23.363			○
7.0	27.257			
8.0	31.151			○
9.0				
10.0	38.938	177.800		○
12.0	46.726			○
14.0				
15.0	58.407			○
16.0				○
18.0				○
20.0	77.876			○
22.0				○
25.0	97.345			○
30.0	116.815			○
35.0				○
40.0				○
45.0				○
50.0				○
60.0				○
70.0				○
80.0				○
90.0				○
100.0				○

黄銅板(BsP)				
板厚	小板定板 365X1200	大板定板 1000X2000	4×8板 1250X2500	切板
0.10	0.369			
0.15	0.554			
0.20	0.738			
0.25	0.923			
0.30	1.108			
0.35	1.292			
0.4	1.477			
0.5	1.846	8.430		
0.6	2.215	10.116		
0.7	2.585	11.802		
0.8	2.954	13.488		
0.9	3.323			
1.0	3.692	16.860	26.344	
1.2	4.431	20.232	31.600	
1.4	5.169			
1.5	5.538	25.290	39.516	
1.6	5.908	26.976		
1.8	6.646			
2.0	7.385	33.720	52.688	
2.3	8.492	38.778		
2.5	9.231	42.150		
2.6	9.600			
2.8	10.338			
3.0	11.077	50.580	79.031	○
3.2	11.815	53.952		
3.5	12.923			
4.0	14.769	67.440		○
4.5	16.615			
5.0	18.462	84.300		○
5.5	20.308			
6.0	22.154	101.160		○
7.0	25.846			○
8.0	29.539			○
9.0	33.231			○
10.0	36.923			○
12.0	44.308			○
14.0				○
15.0	55.385			○
16.0	59.077			○
18.0				○
20.0	73.847			○
22.0				○
25.0	92.308			○
30.0	110.770			○
35.0				○
40.0				○
45.0				○
50.0				○
60.0				○
70.0				○
80.0				○
90.0				○
100.0				○

※銅板の場合 0.1~0.5は無酸素銅(C1020P)及びリン脱酸素銅(C1201P)  
 0.6~10は無酸素銅(C1020P)及びタフピッチ銅(C1100P)  
 12以上はタフピッチ銅(C1100P)。大板、4×8板、切板は全てタフピッチ銅(C1100P)